



## RESIN INFORMATION SHEET

<b>Product Name</b>	<b>TOYOPEARL® Butyl-600M</b> (Hydrophobic interaction chromatography resin)	
<b>Part Numbers</b>	21448	TOYOPEARL Butyl-600M, 25 mL
	21449	TOYOPEARL Butyl-600M, 100 mL
	21450	TOYOPEARL Butyl-600M, 1 L
	21451	TOYOPEARL Butyl-600M, 5 L
	21452	TOYOPEARL Butyl-600M, 50 L
<b>Product Description</b>	<p>TOYOPEARL chromatographic resins are based on a rigid methacrylic polymer, resulting in high mechanical and chemical stability. Resins are available as non-functionalized “HW” series resins for size exclusion separations, and derivatized with surface chemistries for alternative modes of chromatography such as ion exchange, hydrophobic interaction or affinity separations.</p> <p>TOYOPEARL Butyl-600M chromatographic resins are designed for hydrophobic interaction chromatography. This chromatographic mode separates molecules on the basis of hydrophobic interactions between the sample and the ligand. The separation is usually accomplished in buffered aqueous solution with a gradient of decreasing ionic strength.</p>	
<b>Operating Conditions</b>	Packing pressure	Typically 0.3 MPa
	Shipping solvent	20 % (v/v) ethanol
	Shipping formulation	72 % (v/v) slurry in shipping solvent (*)
	Pressure limiting factor	Depend on column hardware (typically 0.7 MPa)
	Operating linear flowrate	Typically 10 - 600 cm/hour
	Long-term storage conditions	20 % (v/v) ethanol
	Cleaning-in-place/Sanitization	0.1 - 0.5 mol/L NaOH or 0.1 mol/L HCl
<b>Specifications</b>	Particle size distribution (min. 80 % within range)	40 - 90 µm
	Protein adsorption capacity (of γ-globulin)	40 - 60 g/L
	Bacterial count	Max. 100 CFU/mL
	Endotoxin concentration	Max. 10.0 EU/mL
	Eluable matter	Max. 0.2 % (for dry gel)
	Foreign substance (colored particle)	Unobserved
<b>Additional Information</b>	Appearance	White resin slurry which settles upon standing
	Mean pore diameter (base resin)	75 nm (*)

(\*) The value is for reference only, not guaranteed.

Lot-specific data are included in the Certificate of Analysis (COA) shipped with the product.  
For detailed test procedures please refer to the appropriate Regulatory Support File.