TOSOH BIOSCIENCE

TOSOH

RESIN INFORMATION SHEET

Product Name	TSKgel® Ether-5PW (Hydrophobic interaction chromatography resin)		
Part Numbers	43276	TSKgel Ether-5PW (20), 25	5 mL
	16052	TSKgel Ether-5PW (20), 25	50 mL
	16053	TSKgel Ether-5PW (20), 1	L
	18437	TSKgel Ether-5PW (20), 5	L
	43176 TSKgel Ether-5PW (30), 25		5 mL
	16050	TSKgel Ether-5PW (30), 250 mL	
	16051	TSKgel Ether-5PW (30), 1	L
	18439	TSKgel Ether-5PW (30), 5	L
Product Description	TSKgel is a methacry	lic polymer with very high n	nechanical and chemical stability.
	chromatographic mo	de separates molecules on t	esigned for hydrophobic interaction chromatography. This he basis of hydrophobic interactions between the sample and the buffered aqueous solution with a gradient of decreasing ionic
Operating	Packing pressure		Typically 1 MPa
Conditions	Shipping solvent		20 % (v/v) ethanol
	Shipping formulation		72 % (v/v) slurry in shipping solvent (*)
	Pressure limiting factor		Depend on column hardware (typically 2 MPa)
	Operating linear flowrate		Typically 60 - 1200 cm/hour (depend on particle size)
	Long-term storage conditions		20 % (v/v) ethanol
	Cleaning-in-place/Sanitization		0.1 - 0.5 mol/L NaOH or 0.1 mol/L HCl
Specifications	Particle size distribution (min. 70 % within range)		15 - 25 μm for (20)-grade 20 - 40 μm for (30)-grade
	Protein adsorption capacity (of Lysozyme)		10 - 30 g/L
	Bacterial count		Max. 100 CFU/mL
	Endotoxin concentration		Max. 10.0 EU/mL
	Eluable matter		Max. 0.2 % (for dry gel)
	Fausing substances	(colored particle)	Unobserved
	Foreign substance	• •	
	Foreign substance		
Additional	Appearance		White resin slurry which settles upon standing

Lot-specific data are included in the Certificate of Analysis (COA) shipped with the product. For detailed test procedures please refer to the appropriate Regulatory Support File.