RESIN INFORMATION SHEET

Product Name	TOYOPEARL® SP-550C (Strong cation exchange chromatography resin)	
Part Numbers	43272	TOYOPEARL SP-550C, 100 mL
	14028	TOYOPEARL SP-550C, 250 mL
	14705	TOYOPEARL SP-550C, 1 L
	14029	TOYOPEARL SP-550C, 5 L
	18366	TOYOPEARL SP-550C, 50 L

Product Description

TOYOPEARL chromatographic resins are based on a rigid methacrylic polymer, resulting in high mechanical and chemical stability. Resins are available as non-functionalized "HW" series resins for size exclusion separations, and derivatized with surface chemistries for alternative modes of chromatography such as ion exchange, hydrophobic interaction or affinity separations.

TOYOPEARL SP-550 chromatographic resin is designed for cation exchange chromatography. This chromatographic mode separates molecules on the basis of ionic interactions between the sample and the resin. The separation is usually accomplished in buffered aqueous solution with a gradient of increasing ionic strength. Alternatively, pH adjustment may be used for control of elution.

Operating Conditions

Typically 0.3 MPa
20 % (v/v) ethanol
72 % (v/v) slurry in shipping solvent (*)
Depend on column hardware (typically 0.7 MPa)
Typically 10 - 600 cm/hour
20 % (v/v) ethanol
0.1 - 0.5 mol/L NaOH or 0.1 mol/L HCl

Specifications

Particle size distribution (Min. 80 % within range)	50 - 150 μm for C-grade
lon exchange capacity	0.14 -0.18 eq/L
Protein adsorption capacity (of lysozyme)	80 - 120 g/L
Bacterial count	Max. 100 CFU/mL
Endotoxin concentration	Max. 10.0 EU/mL
Eluable matter	Max. 0.2 % (for dry gel)
Foreign substance (colored particle)	Unobserved
_	

Additional Information

	Appearance	White resin slurry which settles upon standing
	Mean pore diameter (base resin)	50 nm (*)
-		(*) The value is for reference only not guaranteed

Lot-specific data are included in the Certificate of Analysis (COA) shipped with the product. For detailed test procedures please refer to the appropriate Regulatory Support File.